



ENGINEERING & TECHNICAL DATA — Flex-Tube® EF

INSIDE DIAMETER (IN)	APPROX. WEIGHT (LBS/FT)	WALL THICKNESS (IN)	CL BEND RADIUS (IN)	COMPRESSION RATIO	NEGATIVE PRESSURE (IN/HG)	WORKING PRESSURE (PSI)
2.5	.3	.028	4.6	1.9:1	26	20
3	.35	.028	3.8	1.8:1	22	15
4	.51	.028	4.8	2:1	20	12
5	.62	.030	5.75	2:1	18	11
6	.78	.035	6.75	2:1	16	10
7	.82	.035	7.75	2:1	13	9
8	1.1	.035	8.5	2:1	12	8
10	1.4	.035	10	2:1	6	7

Technical data based on 2 ft. straight lengths of hose @ 72°

Construction: Medium weight coextruded polyolefin elastomer hose with a rigid external polypropylene helix

Temperature Range: -40°F to 225°F

Standard Color: Clear with Green Helix

Standard Lengths: 25 & 50 Feet

Disclaimer: The proper use and maintenance of hose and/or ducting manufactured by Flexaust is the sole responsibility of the purchaser and ultimate user of the product. This information is presented as a general guide only. The number of variables which can be present in any application make firm recommendations impossible.

Tel: 574-267-7909 • Toll Free Tel: 800-343-0428 • Toll Free Fax: 800-382-8464
sales@flexaust.com • www.flexaust.com

